



SPECIFICATION SHEET

Nitrile bonded Cork

Polymer – Chloroprene Rubber. Colour - Black

Properties	Test Method	Results
Hardness (shore type A)		60-80
Compressibility (400 psi)		25% to 40%
Recovery (400 psi)		Min 75%
Tensile strength		Min 1.73 MPa
Density		Min 700 Kg/m ³
Flexibility factor		F=(5)
Volume change -		
70h at 100°C (212°F)	ASTM #1	-10 to 10%
70h at 100°C (212°F)	IRM 903	0% to 20%
22h at RT	Fuel A	0% to 15%
Compression set 22h at 70°C		Max 40%

THIS PRODUCT IS ROHS COMPLIANT

QUALITY ASSURED PRODUCTS WITH FULL TRACEABILITY

Care should be taken in selecting the most suitable quality for each application.

Advice is available but final responsibility remains with the customer.