



SPECIFICATION SHEET

EXT005 – Nitrile tank strap

Properties	Test Method	Results	Unit
Durometer Hardness	68-78	74	IRHD
Tensile Strength	-	9.7	mPa
Elongation at break	-	219	%
Compression set, max 22h at 100°C	ASTM D395 Test method B	46.2	%

QUALITY ASSURED PRODUCTS WITH FULL TRACEABILITY

Care should be taken in selecting the most suitable quality for each application.

Advice is available but final responsibility remains with the customer.