



## SPECIFICATION SHEET

### FNE-AL43 Natural Epdm Foam

Property	Test Method	Typical Value	Unit
Compression set (23 +/- 2°C, 22h, 50% compression): Measure after 24h	ASTM D 1056	≤16	%
Density	ASTM D 3575	300	g/cm <sup>3</sup>
Water absorption Max weight change	ASTM D 1056	≤2 Vol	
Temperature range	-	-30 to +100	°C
High intermittent	-	180	°C
Tensile strength	ASTM D 42	1050	kPa
Elongation Minimum	ASTM D 412	≥230	%
Hardness shore 00	-	60 – 65	°
Flammability rate	FMVSS302	Approved	-

**The above figures are average values and should be considered as guidelines not specifications.**

**While reasonable care has been taken to ensure that this data is representative, Cutting Industries Ltd does not warrant or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability or completeness of the information.**

**We recommend evaluation prior to use to ascertain the suitability of the material for the application.**