



SPECIFICATION SHEET

PP-ABS Black Pin seal ABS

Properties	Unit	Test Method	Result
Density	-	g/cm ³	1.06 – 1.08
Vicat Softening Temperature	ISO 306	°C	95
Heat Deflection temperature	ISO 75	°C	93
Tensile Strength	ISO 527	mPa	42
Flexural Strength	ISO 178	mPa	69
Izod impact Strength – notched	ISO 180	KJ/m ²	19
Moulding Shrinkage	-	%	0.6-0.8
Forming temperature	-	°C	150 – 185
Fire rating	UL94	-	HB

QUALITY ASSURED PRODUCTS WITH FULL TRACEABILITY

Care should be taken in selecting the most suitable quality for each application.

Advice is available but final responsibility remains with the customer.