



SPECIFICATION SHEET

R-098 V99 Viton A

SPECIFICATION	RESULT
Elastomer	FKM Viton® Compounded from Chemours Viton
Colour	Black
Quality	Viton A
Grade	V99
Hardness ISO 7619-1	70° shore A +/- 5°
S.G (g/cm <sup>3</sup> ) ISO 2781	1.85
Tensile (N/mm <sup>2</sup> ) ISO 37	7
Elongation (%) ISO 37	220
Compression (%) ISO 37	55 175° @ 22hrs
Temperature range (°C)	-20° to 250°

THIS PRODUCT IS ROHS COMPLIANT

**QUALITY ASSURED PRODUCTS WITH FULL TRACEABILITY**

Care should be taken in selecting the most suitable quality for each application.

Advice is available but final responsibility remains with the customer.