

FDA Compliant Solid Silicone Elastomer Rolls

Our general-purpose range of silicone rolls. The range has been tested to and is in compliance with the American Food and Drugs Administration (FDA) 21 CFR 177-2600, BfR XV Empfehlung and colour bleed test according to BfR-Empfehlung part B 11 & Directive EC 1935/2004.

Translucent, Blue, White, Red and Black 40° to 70° Shore.

Additional compliance:

These products meet the flammability requirements of FAR 25/JAR 25/CS 25 Appendix F, Part 1, (a)(1)(iv) and (a)(1)(v) horizontal flammability tests and Automotive Standard PART 571FMVSS302.

Environmental Resistance:

Silicone rubber products have an excellent resistance to ozone, oxidation, ultraviolet light, corona discharge, cosmic radiation, ionising radiation and weathering in general.



Temperature Range:

-60°C (-76°F) to +230°C (+446°F)
and up to 250°C (482°F) intermittent.

Availability:

- Widths of 1200mm (standard), 1500mm and 1800mm.
- Pressure sensitive adhesive backing.
- Custom cut gaskets.
- Standard colours: Red Iron Oxide, Black, White, Blue.
- Translucent available at extra cost.
- Capability to colour match.

PROPERTY	UNITS	JFGP30	JFGP40	JFGP50	JFGP60	JFGP70	JFGP80	TEST METHOD
		TYPICAL VALUE	TYPICAL VALUE	TYPICAL VALUE	TYPICAL VALUE	TYPICAL VALUE	TYPICAL VALUE	
Hardness	Shore A (±5)	30	40	50	60	70	80	DIN ISO 7619-1
Tensile Strength	MPa psi	8.0 1150	9.0 1300	9.0 1300	10.0 1450	10.0 1450	7.0 1015	ISO 37 type 2
Elongation to Failure	%	500	525	450	400	320	215	ISO 37 type 2
Tear Strength	N/mm (lb/in.)	16.0 91	23 130	18 100	22 125	20 115	17 88.5	ASTM D624 die B
Compression Set 24 hours @150°C	%	23	25	15	13	9	18	DIN/ISO 815 type B
Compression Set 22 hours @300°C	%	20	22	16	10	10	16	ASTM D395 method B type 2

Standard stock offering is 60° Shore, in thicknesses 0.3mm to 12mm (other thicknesses to order)
For 40° translucent: our standard stock offerings are thicknesses 1mm to 8mm

continued on page 2

Dimensional Tolerances: are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

Disclaimer: All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.

FDA Compliant Solid Silicone Elastomer Rolls

TEST	RESULT	STANDARD
Brittle Point	-80°C (-112 °F)	ASTM D746
Limiting Oxygen Index	24.0%	BS 2782 Part 1
Thermal Conductivity	0.24 W.m ⁻¹ .K ⁻¹	VDE 0304
Radiation Resistance	>10 ⁵ Grays (10 ⁷ Rads) typical	
Dielectric Strength	23 kV.mm ⁻¹	VDE 0303
Dielectric Constant	2.9	VDE 0303
Dissipation Factor	3x10 ⁻⁴	VDE 0303
Volume Resistivity	3x10 ¹⁵ Ω.cm	VDE 0303

Dimensional Tolerances:

THICKNESS (mm)	ST2
0 - 1	±0.2
1 - 1.6	±0.25
1.6 - 2.5	±0.35
2.5 - 4	±0.4
4 - 6.3	±0.5
6.3 - 10	±0.7
10 - 16	±0.8%

Dimensional Tolerances: are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

Disclaimer: All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.

Issued: Nov 2021

Cutting Industries, Unit 3, 206 Belsize Rd, Lisburn, Co. Antrim N.Ireland BT27 4DT

Tel No. +44 (0) 28 9266 0773 Fax No. +44 (0) 28 9267 9899

Email: sales@cuttingindustries.co.uk Web: www.cuttingindustries.co.uk

