

SPECIFICATION SHEET

X203-5133 Non Cermaic Mill board

Properties	Test method	Unit	Values
Density	-	Kg/m ³	1000
Coefficient of thermal conductivity	-	W/mK	0.1
Tensile Strength	-	mPa @ 20°C	3.4
Flexural Strength	-	mPa @ 20°C	8.0
Compression	-	% @ 21 mPa	35
Moisture content	-	%	1.05
Loss on ignition	-	%	12
Linear shrinkage in 24 hours	-	% @ 1000°C	0.75

QUALITY ASSURED PRODUCTS WITH FULL TRACEABILITY

Care should be taken in selecting the most suitable quality for each application.

Advice is available but final responsibility remains with the customer.